## Polymer Add (Thailand) Co.,Ltd.

Office - 106, Chalaremprakiat, Lor 9, Soi 22, Yak 5, Nongbon, Prawet, Bangkok, Thailand 10250

Factory - 188/3, Moo 8, Tambon Bangpu Mai, Amphoe Muang Samut Prakan, Samutprakan, Thailand 10280

Mobile - Thai: 0804531391, English: 0839415475, E-mail - contact@polymeradd.co.th



# TECHNICAL DATA SHEET KC-258

Chemical Name	KAOLIN CLAY (MICRONIZED)
Grade Name	KC-258
CAS No.	1332-58-7
HS Code	2507.00.00
EINECS No.	310-194-1
Molecular Formula	$Al_2Si_2O_5(OH)_4$
Molecular Weight	258.16 g/mol
Synanyma	Kaolinite, Hydrated Aluminium Silicate, China Clay, White
Synonyms	Clay

Property	Typical Value / Description	Test Method
Appearance	Fine white to off-white powder	Visual
Odor	Odourless	Sensory
pH (10% slurry)	4.0 – 6.0	pH meter
Moisture Content	≤ 1.0%	Oven drying (110 Deg C) till constant weight
Bulk Density	0.3 – 0.5 g/cm <sup>3</sup>	Tapped Density Method
Whiteness	≥ 88	CIE method (paste in mineral oil base)
Oil Absorption (DBP)	30 – 45 g/100g	Spatula Rub-Out Method
Melting Point	>1600°C (decomposes)	Literature / Estimation
Solubility in Water	Insoluble	Visual observation
Loss on Ignition (LOI)	12 - 15% (at 1000°C)	Heating in muffle furnace 900°C
Particle Size (D50)	Typically, 5 µm (grade-dependent)	Laser Diffraction (Wet method)
Particle Size (D99)	Typically, 20 µm (grade-dependent)	Laser Diffraction (Wet method)

<sup>&</sup>gt; The commercial product specification may include only a selection of the properties listed above; this additional data is provided for general technical reference.

Heavy Metals (EU Regulation 10/2011 (content limits in additives)			
Plastics (Food-Grade / Repeated Use)			
Element	Typical Limit	Test Method	
Lead (Pb)	≤ 10 ppm	ICP, AAS, XRF	
Cadmium (Cd)	≤ 1 ppm	ICP, AAS	
Mercury (Hg)	≤ 0.1 – 1 ppm	ICP, AAS, CV-AAS	
Arsenic (As)	≤ 1 – 3 ppm	ICP, AAS	
Chromium (VI)	ND – 0.1 ppm (if present)	UV-Vis (after extraction with NaOH)	

# Polymer Add (Thailand) Co.,Ltd.

Office - 106, Chalaremprakiat, Lor 9, Soi 22, Yak 5, Nongbon, Prawet, Bangkok, Thailand 10250

Factory - 188/3, Moo 8, Tambon Bangpu Mai, Amphoe Muang Samut Prakan, Samutprakan, Thailand 10280

Mobile - Thai: 0804531391, English: 0839415475, E-mail - contact@polymeradd.co.th



Colour impacting impurities		
Element	Typical Max Limit (ppm)	Test Method
Iron (Fe)	≤ 3000 ppm	ICP, AAS, XRF
Manganese (Mn)	≤ 100 ppm	ICP, AAS, XRF
Chromium (Cr)	≤ 50 ppm	ICP, AAS, XRF
Copper (Cu)	≤ 50 ppm	ICP, AAS, XRF
Nickel (Ni)	≤ 30 ppm	ICP, AAS, XRF
Cobalt (Co)	≤ 20 ppm	ICP, AAS, XRF
Vanadium (V)	≤ 20 ppm	ICP, AAS, XRF

Product performance impacting impurities		
Ion / Element	Typical Max Limit (ppm)	Test Method
Calcium (Ca)	≤ 500 ppm	ICP, AAS, XRF
Magnesium (Mg)	≤ 300 ppm	ICP, AAS, XRF
Sodium (Na)	≤ 300 ppm	ICP, AAS, XRF
Potassium (K)	≤ 200 ppm	ICP, AAS, XRF
Chloride (Cl <sup>-</sup> )	≤ 100 ppm	Ion Chromatography
Sulphate (SO <sub>4</sub> <sup>2-</sup> )	≤ 100 ppm	Ion Chromatography
Titanium (Ti)	≤ 150 ppm	ICP, AAS, XRF

#### **USES / APPLICATION**

Industry	Commercial Application / Uses (Micronized Grade)
Plastics	Filler and extender in PVC, polyolefins, and engineering plastics; improves
Plastics	rigidity and dimensional stability
Rubber	Reinforcing filler in natural and synthetic rubber; enhances processing and
Lunnei	surface smoothness
Paints & Coatings	Opacity enhancer, anti-settling agent, extender for TiO <sub>2</sub> in architectural and
	industrial paints
Danas (Capting Crada)	Surface coating and filler to improve printability, smoothness, and
Paper (Coating Grade)	brightness in high-grade papers
Adhesives & Sealants	Rheology control, anti-sagging agent, filler to enhance mechanical
	properties and reduce shrinkage
Inks	Viscosity modifier and extender in solvent- and water-based printing inks;
IIIVO	improves print sharpness

#### **US FDA 21 CFR LISTING**

<b>CFR Section</b>	Title / Description
176.170	Components of paper and paperboard in contact with aqueous and fatty foods
176.180	Components of paper and paperboard in contact with dry foods
177.1200	Cellophane (permitted as filler or adjuvant in cellophane intended for food contact)
177.2260	Filters, resin-bonded (used as inert mineral filler in bonded filters for food use)

### Polymer Add (Thailand) Co.,Ltd.

Office - 106, Chalaremprakiat, Lor 9, Soi 22, Yak 5, Nongbon, Prawet, Bangkok, Thailand 10250

Factory - 188/3, Moo 8, Tambon Bangpu Mai, Amphoe Muang Samut Prakan, Samutprakan, Thailand 10280

Mobile - Thai: 0804531391, English: 0839415475, E-mail - contact@polymeradd.co.th



Kaolin is recognized as GRAS (Generally Recognized As Safe) under certain conditions. Actual applicability depends on final formulation and exposure conditions.

#### Disclaimer:

This product is manufactured according to industrial mineral standards. Although impurity levels comply with general safety limits for use in plastics and coatings, buyers must request specific certification if intended for food-contact or pharmaceutical applications. Not intended for medical implants or long-term contact with mucosa.

Month of Creation: June 2025 Month of Review: June 2027