

Polymer Add (Thailand) Co.,Ltd.

Office - 106, Chalaremprikiat, Lor 9, Soi 22, Yak 5, Nongbon, Prawet, Bangkok, Thailand 10250

Factory - 188/3, Moo 8, Tambon Bangpu Mai, Amphoe Muang Samut Prakan, Samutprakan, Thailand 10280


Mobile - Thai : 0804531391, English: 0839415475, E-mail - contact@polymeradd.co.th



PARTICLE SIZE ANALYSIS RESULT

MICRONISED SUCROSE BENZOATE

D50	D90	D99	D100
3.20 µm	9.36 µm	17.62 µm	27.47 µm



Diam um	Diff%	Cumu%	Diam um	Diff%	Cumu%	Diam um	Diff%	Cumu%	Diam um	Diff%	Cumu%
0.000 - 0.100	0.72	0.72	0.848 - 0.944	1.71	15.25	8.021 - 8.926	3.02	88.85	75.78 - 84.33	0	100
0.100 - 0.111	0.17	0.89	0.944 - 1.051	1.9	17.15	8.926 - 9.933	2.65	91.5	84.33 - 93.85	0	100
0.111 - 0.123	0.18	1.07	1.051 - 1.170	2.1	19.25	9.933 - 11.05	2.21	93.71	93.85 - 104.4	0	100
0.123 - 0.137	0.2	1.27	1.170 - 1.302	2.29	21.54	11.05 - 12.30	1.8	95.51	104.4 - 116.2	0	100
0.137 - 0.153	0.25	1.52	1.302 - 1.449	2.52	24.06	12.30 - 13.69	1.43	96.94	116.2 - 129.3	0	100
0.153 - 0.170	0.25	1.77	1.449 - 1.612	2.74	26.8	13.69 - 15.23	1.08	98.02	129.3 - 143.9	0	100
0.170 - 0.189	0.3	2.07	1.612 - 1.794	2.99	29.79	15.23 - 16.95	0.79	98.81	143.9 - 160.2	0	100
0.189 - 0.211	0.35	2.42	1.794 - 1.997	3.23	33.02	16.95 - 18.87	0.54	99.35	160.2 - 178.2	0	100
0.211 - 0.235	0.39	2.81	1.997 - 2.222	3.46	36.48	18.87 - 21.00	0.36	99.71	178.2 - 198.4	0	100
0.235 - 0.261	0.43	3.24	2.222 - 2.473	3.71	40.19	21.00 - 23.37	0.18	99.89	198.4 - 220.8	0	100
0.261 - 0.291	0.51	3.75	2.473 - 2.752	3.93	44.12	23.37 - 26.00	0.09	99.98	220.8 - 245.7	0	100
0.291 - 0.324	0.55	4.3	2.752 - 3.063	4.11	48.23	26.00 - 28.94	0.02	100	245.7 - 273.4	0	100
0.324 - 0.360	0.61	4.91	3.063 - 3.409	4.25	52.48	28.94 - 32.21	0	100	273.4 - 304.3	0	100
0.360 - 0.401	0.71	5.62	3.409 - 3.794	4.38	56.86	32.21 - 35.84	0	100	304.3 - 338.6	0	100
0.401 - 0.446	0.77	6.39	3.794 - 4.222	4.44	61.3	35.84 - 39.89	0	100	338.6 - 376.9	0	100
0.446 - 0.497	0.9	7.29	4.222 - 4.699	4.45	65.75	39.89 - 44.39	0	100	376.9 - 419.4	0	100
0.497 - 0.553	0.99	8.28	4.699 - 5.229	4.39	70.14	44.39 - 49.40	0	100	419.4 - 466.8	0	100
0.553 - 0.615	1.11	9.39	5.229 - 5.819	4.28	74.42	49.40 - 54.98	0	100	466.8 - 519.4	0	100
0.615 - 0.685	1.24	10.63	5.819 - 6.476	4.09	78.51	54.98 - 61.19	0	100	519.4 - 578.1	0	100
0.685 - 0.762	1.37	12	6.476 - 7.207	3.83	82.34	61.19 - 68.09	0	100	578.1 - 643.3	0	100
0.762 - 0.848	1.54	13.54	7.207 - 8.021	3.49	85.83	68.09 - 75.78	0	100	643.3 - 716.0	0	100