

# Polymer Add (Thailand) Co.,Ltd.


Office - 106, Chalaremprikiat, Lor 9, Soi 22, Yak 5, Nongbon, Prawet, Bangkok, Thailand 10250  
 Factory - 188/3, Moo 8, Tambon Bangpu Mai, Amphoe Muang Samut Prakan, Samutprakan, Thailand 10280  
 Mobile - Thai : 0804531391, English: 0839415475, E-mail – contact@polymeradd.co.th



## PARTICLE SIZE ANALYSIS RESULT

### ZINC BENZOATE

<b>D50</b>	<b>D90</b>	<b>D99</b>	<b>D100</b>
3.02 µm	11.88 µm	24.65 µm	39.08 µm



Diam um	Diff%	Cumu%									
0.000 - 0.100	0.48	0.48	0.848 - 0.944	1.82	23.07	8.021 - 8.926	3.07	83.22	75.78 - 84.33	0	100
0.100 - 0.111	0.32	0.8	0.944 - 1.051	1.91	24.98	8.926 - 9.933	2.8	86.02	84.33 - 93.85	0	100
0.111 - 0.123	0.38	1.18	1.051 - 1.170	1.98	26.96	9.933 - 11.05	2.5	88.52	93.85 - 104.4	0	100
0.123 - 0.137	0.46	1.64	1.170 - 1.302	2.02	28.98	11.05 - 12.30	2.22	90.74	104.4 - 116.2	0	100
0.137 - 0.153	0.58	2.22	1.302 - 1.449	2.12	31.1	12.30 - 13.69	1.96	92.7	116.2 - 129.3	0	100
0.153 - 0.170	0.6	2.82	1.449 - 1.612	2.2	33.3	13.69 - 15.23	1.68	94.38	129.3 - 143.9	0	100
0.170 - 0.189	0.7	3.52	1.612 - 1.794	2.29	35.59	15.23 - 16.95	1.45	95.83	143.9 - 160.2	0	100
0.189 - 0.211	0.79	4.31	1.794 - 1.997	2.4	37.99	16.95 - 18.87	1.22	97.05	160.2 - 178.2	0	100
0.211 - 0.235	0.86	5.17	1.997 - 2.222	2.49	40.48	18.87 - 21.00	0.98	98.03	178.2 - 198.4	0	100
0.235 - 0.261	0.93	6.1	2.222 - 2.473	2.62	43.1	21.00 - 23.37	0.72	98.75	198.4 - 220.8	0	100
0.261 - 0.291	1.03	7.13	2.473 - 2.752	2.76	45.86	23.37 - 26.00	0.51	99.26	220.8 - 245.7	0	100
0.291 - 0.324	1.08	8.21	2.752 - 3.063	2.89	48.75	26.00 - 28.94	0.35	99.61	245.7 - 273.4	0	100
0.324 - 0.360	1.15	9.36	3.063 - 3.409	3.02	51.77	28.94 - 32.21	0.22	99.83	273.4 - 304.3	0	100
0.360 - 0.401	1.24	10.6	3.409 - 3.794	3.2	54.97	32.21 - 35.84	0.12	99.95	304.3 - 338.6	0	100
0.401 - 0.446	1.28	11.88	3.794 - 4.222	3.36	58.33	35.84 - 39.89	0.05	100	338.6 - 376.9	0	100
0.446 - 0.497	1.4	13.28	4.222 - 4.699	3.54	61.87	39.89 - 44.39	0	100	376.9 - 419.4	0	100
0.497 - 0.553	1.45	14.73	4.699 - 5.229	3.69	65.56	44.39 - 49.40	0	100	419.4 - 466.8	0	100
0.553 - 0.615	1.51	16.24	5.229 - 5.819	3.77	69.33	49.40 - 54.98	0	100	466.8 - 519.4	0	100
0.615 - 0.685	1.61	17.85	5.819 - 6.476	3.77	73.1	54.98 - 61.19	0	100	519.4 - 578.1	0	100
0.685 - 0.762	1.66	19.51	6.476 - 7.207	3.64	76.74	61.19 - 68.09	0	100	578.1 - 643.3	0	100
0.762 - 0.848	1.74	21.25	7.207 - 8.021	3.41	80.15	68.09 - 75.78	0	100	643.3 - 716.0	0	100